

# Karina WHITE PVC COMPOUND 851-10/1-E-IS

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

## Message:

PVC COMPOUND CLASS 70C (PVC/F) RECOMMENDED FOR INSULATION OF ELECTRICAL WIRES AND FLEXIBLE CORDS. ALSO SUITABLE FOR EXTRUSION OF NON STANDARD COAXIAL CABLE JACKET.

| General Information                     |                                 |                   |               |
|-----------------------------------------|---------------------------------|-------------------|---------------|
| Uses                                    | Cable Jacketing                 |                   |               |
|                                         | Electronic Insulation           |                   |               |
|                                         | Wire & Cable Applications       |                   |               |
| Appearance                              | White                           |                   |               |
| Processing Method                       | Extrusion                       |                   |               |
| Physical                                | Nominal Value                   | Unit              | Test Method   |
| Density <sup>1</sup>                    | 1.43 to 1.47                    | g/cm <sup>3</sup> | IEC 60811-1-3 |
| Color                                   | OK                              |                   | ME 12         |
| Color a                                 | -1.70 to 0.300                  |                   | ME 12         |
| Color b                                 | 0.570 to 2.57                   |                   | ME 12         |
| Color L                                 | 90.5 to 92.5                    |                   | ME 12         |
| Maximum Variation of Elongation         | < 20                            | %                 | IEC 60811-1-2 |
| Maximum Variation of Tensile Strength   | < 20                            | %                 | IEC 60811-1-2 |
| Hardness                                | Nominal Value                   | Unit              | Test Method   |
| Durometer Hardness (Shore A, 15 sec)    | 84 to 88                        |                   | NBR 7456      |
| Mechanical                              | Nominal Value                   | Unit              | Test Method   |
| Tensile Stress                          | > 10.0                          | MPa               | IEC 60811-1-1 |
| Tensile Strain (Yield)                  | > 150                           | %                 | IEC 60811-1-1 |
| Elastomers                              | Nominal Value                   | Unit              | Test Method   |
| Tensile Strength <sup>2</sup>           | > 10.0                          | MPa               | IEC 60811-1-2 |
| Tensile Elongation <sup>3</sup> (Break) | > 150                           | %                 | IEC 60811-1-2 |
| Thermal                                 | Nominal Value                   | Unit              | Test Method   |
| Brittleness Temperature                 | < -15.0                         | °C                | ASTM D746     |
| Electrical                              | Nominal Value                   | Unit              | Test Method   |
| Volume Resistivity <sup>4</sup>         | > 1.0E+14                       | ohms · cm         | NBR 5403      |
| NOTE                                    |                                 |                   |               |
| 1.                                      | 24 hr                           |                   |               |
| 2.                                      | Aged in Air for 168 hr at 100°C |                   |               |
| 3.                                      | Aged in Air for 168 hr at 100°C |                   |               |
| 4.                                      | 24 hr                           |                   |               |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

