

Integra™ PBT-4130

Polybutylene Terephthalate

PolySource, LLC

Message:

PBT, High Viscosity, Natural

General Information			
Features	Viscosity, High		
Appearance	Natural color		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.30 - 1.32	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	4.0 - 7.0	g/10 min	ISO 1133
Molding Shrinkage	1.2 - 1.8	%	ISO 294-4
Viscosity Number (Reduced Viscosity)	128.0 - 132.0	ml/g	ISO 1628
Moisture Content		%	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	49.0 - 58.6	MPa	ISO 527-2
Tensile Strain (Break)	> 180	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	> 59	J/m	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	155	°C	ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ISO 75-2/A
Melting Temperature	225	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Dielectric Strength (2.00 mm)	> 20	kV/mm	IEC 60243-1
Arc Resistance	120	sec	UL 746
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	240 - 265	°C	
Cylinder Zone 3 Temp.	240 - 265	°C	
Cylinder Zone 5 Temp.	240 - 265	°C	
Die Temperature	250 - 265	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT