

LUVOCOM® 19-8942

Polyamide 46
Lehmann & Voss & Co.

Message:

LUVOCOM® 19-8942 is a polyamide 46 (nylon 46) material. This product is available in Europe.
LUVOCOM®The main features of 19-8942 are:
Wear-resistant
Lubrication
Typical application areas include:
engineering/industrial accessories
Electrical/electronic applications
textile/fiber
Automotive Industry
business/office supplies

General Information			
Additive	PTFE lubricant		
Features	Low friction coefficient		
	Good wear resistance		
	Lubrication		
Uses	Gear		
	Textile applications		
	Engineering accessories		
	Switch		
	Application in Automobile Field		
	Business equipment		
	Bearing		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183
Molding Shrinkage	1.3 - 2.0	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3500	MPa	ISO 527-2
Tensile Stress (Break)	75.0	MPa	ISO 527-2
Tensile Strain (Yield)	7.0	%	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress	97.0	MPa	ISO 178
Flexural Strain at Flexural Strength	7.8	%	ISO 178
Maximum operating temperature-Short Term	160	°C	

Insulation Resistance	> 1.0E+12	ohms	IEC 60167
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	130	kJ/m ²	ISO 179/1fU
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	150	°C	UL 746B
Injection	Nominal Value	Unit	
Drying Temperature			
A	80.0	°C	
Vacuum dryer, B	80.0	°C	
Drying Time			
A	2.0 - 8.0	hr	
Vacuum dryer, B	2.0 - 12	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	285 - 315	°C	
Middle Temperature	305 - 315	°C	
Front Temperature	305 - 315	°C	
Nozzle Temperature	280 - 330	°C	
Processing (Melt) Temp	310	°C	
Mold Temperature	120 - 140	°C	
Injection instructions			

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing the moisture level should not exceed 0.1%, otherwise molecular degradation and surface defects (e.g. smearing) may occur. As the material absorbs water very rapidly, originally sealed containers should only be opened immediately before processing. Excessively high predrying temperatures may cause discoloration.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

