

NILENE® P3 K30VA

Polypropylene Homopolymer

Taro Plast S.p.A.

Message:

Polypropylene homopolymer 30% glass fibers reinforced chemically coupled, low flow, good mechanical properties.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Chemical coupling		
	Homopolymer		
	Low liquidity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction	0.70 - 0.90	%	Internal method
Flow direction	0.20 - 0.40	%	Internal method
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000	MPa	ISO 527-2/1
Tensile Stress (Break)	90.0	MPa	ISO 527-2/50
Tensile Strain (Break)	3.5	%	ISO 527-2/50
Flexural Modulus ¹	5600	MPa	ISO 178
Flexural Stress ²	125	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	70	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	153	°C	ISO 75-2/B
1.8 MPa, not annealed	148	°C	ISO 75-2/A
Vicat Softening Temperature			
--	155	°C	ISO 306/A50
--	134	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Burning Rate ³ (2.00 mm)	< 100	mm/min	ISO 3795
Flame Rating (1.60 mm)	HB		UL 94
Oxygen Index	20	%	ASTM D2863
Additional Information	Nominal Value	Unit	Test Method
Reinforcement Content ⁴ (600°C)	30	%	ISO 3451
Injection	Nominal Value	Unit	
Processing (Melt) Temp	220 - 250	°C	
Mold Temperature	50.0 - 70.0	°C	
Injection Rate	Moderate		
Injection instructions			
Pre-heat Temperature: 70 to 80°CPre-heat Time: 1 hr			
NOTE			
1.	1.0 mm/min		
2.	1.0 mm/min		
3.	US FMVSS302		
4.	1 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT