Chemiton GA H2NA 85

Styrene Ethylene Butylene Styrene Block Copolymer Franplast S.r.l.

Message:

Self-extinguishing SEBS based compound endowed with good mechanical properties and dimensional stability. It can be used for several kinds of application especially in the electrical field.

Application:

Gaskets to be Applied on Cables (Electrical Field)

General Information			
Features	Good Dimensional Stability		
	Self Extinguishing		
Uses	Electrical/Electronic Applications		
	Gaskets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	30	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	85		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	6.50	MPa	ISO 527-2
Nominal Tensile Strain at Break	650	%	ISO 527-2
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	35	kN/m	ISO 34-1
Thermal	Nominal Value	Unit	
Service Temperature	-30 to 90	°C	
Injection	Nominal Value	Unit	
Drying Time	0.0	hr	
Rear Temperature	165 to 195	°C	
Middle Temperature	175 to 205	°C	
Front Temperature	185 to 215	°C	
Nozzle Temperature	195 to 225	°C	
Mold Temperature	30.0 to 60.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

