

CYCOLAC™ MG47 resin

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

Multi-purpose, injection molding ABS providing a favorable balance of engineering properties.

General Information			
UL YellowCard	E45329-102071277	E45329-102071276	
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
230°C/3.8 kg	5.6	g/10 min	ASTM D1238
220°C/10.0 kg	18	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.80	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2270	MPa	ASTM D638
--	2370	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	44.0	MPa	ASTM D638
Yield	47.0	MPa	ISO 527-2/50
Fracture ³	33.0	MPa	ASTM D638
Fracture	35.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	2.0	%	ASTM D638
Yield	2.6	%	ISO 527-2/50
Fracture ⁵	24	%	ASTM D638
Fracture	25	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2300	MPa	ASTM D790
-- ⁷	2200	MPa	ISO 178
Flexural Stress			
--	70.0	MPa	ISO 178
Yield, 50.0mm span ⁸	70.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA

-30°C	9.0	kJ/m ²	ISO 179/1eA
23°C	26	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C	320	J/m	ASTM D256
-30°C ¹⁰	8.0	kJ/m ²	ISO 180/1A
23°C ¹¹	22	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	30.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	94.0	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	80.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	81.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	99.0	°C	ASTM D1525 ¹³
--	98.0	°C	ISO 306/B50
--	100	°C	ISO 306/B120
Ball Pressure Test (75°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	8.8E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	8.8E-5	cm/cm/°C	ASTM E831
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI	60.0	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ¹⁴	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 0		UL 746
High Amp Arc Ignition (HAI)	PLC 0		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (240°C, 1000 sec ⁻¹)	225	Pa · s	ASTM D3835
Injection	Nominal Value	Unit	
Drying Temperature	82.2 - 93.3	°C	
Drying Time	2.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.10	%	
Suggested Shot Size	50 - 70	%	
Rear Temperature	188 - 210	°C	
Middle Temperature	204 - 227	°C	

Front Temperature	216 - 238	°C
Nozzle Temperature	218 - 260	°C
Processing (Melt) Temp	218 - 260	°C
Mold Temperature	48.9 - 71.1	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	30 - 60	rpm
Vent Depth	0.038 - 0.051	mm

NOTE

1.	5.0 mm/min
2.	Type 1, 5.0 mm/min
3.	Type 1, 5.0 mm/min
4.	Type 1, 5.0 mm/min
5.	Type 1, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	标准 B (120°C/h), 载荷2 (50N)
14.	Tungsten electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT