ADENE NCWA

Polypropylene Homopolymer

A.D. Compound spa

Message:

ADENE NCWA is a polypropylene homopolymer (PP Homopoly) material, which contains 60% calcium carbonate filler. This product is available in North America or Europe. The main characteristics of ADENE NCWA are: homopolymer.

General Information			
Filler / Reinforcement	Pearl filler, 60% packing by weight		
Features	Homopolymer		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.50	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	20	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	75		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	15.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	3.0	%	ISO 527-2
Fracture	20	%	ISO 527-2
Flexural Modulus	3200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	2.4	kJ/m²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	5.0	kJ/m²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa,			
Unannealed)	70.0	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306
Additional Information			
Residue Calcination ISO 3451: 60%			

Residue Calcination, ISO 3451: 60%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

