SABIC® PP 49MK45

Polypropylene Impact Copolymer

SABIC Americas, Inc.

Message:

Product Description

PP 49MK45 is specially developed for producing injection molded articles. This grade contains nucleating- & antistatic agents. It has medium flow properties , good impact resistance (even at low temperature) and good stiffness.

Typical Applications

PP 49MK45 can be used for houseware, garden furniture , toys, containers & pails.

General Information				
Additive	Antistatic			
	Nucleating Agent			
Features	Antistatic			
	High Stiffness			
	Impact Copolymer			
	Low Temperature Impact Resistance			
	Medium Flow			
	Medium Impact Resistance			
	Nucleated			
Uses	Containers			
	Household Goods			
	Outdoor Applications			
	Outdoor Furnishings			
	Pails			
	Toys			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.905	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (230°C/2.16	21	g/10 min	ASTM D1238	
kg) Molding Shrinkage	1.2 to 2.5	%		
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness (R-Scale, Injection		Chit		
Molded)	98		ASTM D785	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Modulus - 1% Secant (Injection Molded)	1500	MPa	ASTM D638	
Tensile Strength (Yield, Injection Molded)	27.0	MPa	ASTM D638	

Tensile Elongation (Yield, Injection			
Molded)	7.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C, Injection Molded	50	J/m	
23°C, Injection Molded	85	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45		
MPa, Unannealed)	105	°C	ASTM D648
Vicat Softening Temperature	151	°C	ASTM D1525 ¹
Injection	Nominal Value	Unit	
Rear Temperature	200 to 250	°C	
Middle Temperature	200 to 250	°C	
Front Temperature	200 to 250	°C	
Mold Temperature	15.0 to 40.0	°C	
NOTE			
1.	Rate B (120°C/h)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

