TOTAL Polypropylene PPH 3925WZ

Polypropylene Homopolymer TOTAL Refining & Chemicals

Message:

Total Petrochemicals Polypropylene 3925WZ is nucleated to provide fast cycle time and improve contact clarity. 3925WZ contains an antistat that will help protect molded parts from shelf dusting. 3925WZ complies with all applicable FDA regulations for food contact applications. 3925WZ is recommended for thin wall parts, caps and closures in multi-cavity molds.

| General Information | | | | |
|---------------------------------------|--------------------------------------|----------|-------------|--|
| UL YellowCard | E66261-247994 | | | |
| Additive | Antistatic | | | |
| | Nucleating Agent | | | |
| | | | | |
| Features | Antistatic | | | |
| | Contact Clarity | | | |
| | Fast Molding Cycle | | | |
| | Food Contact Acceptable | | | |
| | Good Flow | | | |
| | Good Stiffness | | | |
| | Nucleated | | | |
| | | | | |
| Uses | Caps | | | |
| | Closures | | | |
| | Thin-walled Parts | | | |
| | | | | |
| Agency Ratings | EC 1907/2006 (REACH) | | | |
| | FDA Food Contact, Unspecified Rating | | | |
| | | | | |
| RoHS Compliance | RoHS Compliant | | | |
| Forms | Pellets | | | |
| Processing Method | Injection Molding | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Density | 0.905 | g/cm³ | ASTM D1505 | |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | | |
| kg) | 60 | g/10 min | ASTM D1238 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Rockwell Hardness (R-Scale) | 107 | | ASTM D785 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Modulus | 1790 | MPa | ASTM D638 | |
| Tensile Strength (Yield) | 37.9 | MPa | ASTM D638 | |

| Tensile Elongation (Yield) | 10 | % | ASTM D638 |
|---------------------------------------|---------------|------|-------------|
| Flexural Modulus | 1830 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C) | 21 | J/m | ASTM D256A |
| Unnotched Izod Impact (23°C) | 850 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0. | 45 | | |
| MPa, Unannealed) | 127 | °C | ASTM D648 |
| Melting Temperature | 166 | °C | DSC |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 200 to 232 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

