

INEOS HDPE T50-500-196

High Density Polyethylene Copolymer

INEOS Olefins & Polymers USA

Message:

T50-500-196 is a narrow molecular weight high density polyethylene copolymer intended for injection molding applications where a good balance of processability and end-use properties are required. This material meets the Food and Drug Administration requirements of 21 CFR 177.1520.

General Information			
Features	Copolymer		
	Food Contact Acceptable		
	High Density		
	Narrow Molecular Weight Distribution		
Agency Ratings	EC 1907/2006 (REACH)		
	FDA 21 CFR 177.1520		
RoHS Compliance	Contact Manufacturer		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.953	g/cm ³	ASTM D4883
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (100% Igepal, F50)	7.00	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	68		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	27.2	MPa	
Break	26.2	MPa	
Tensile Elongation ²			ASTM D638
Yield	10	%	
Break	> 1000	%	
Flexural Modulus - Tangent	1300	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	45	J/m	ASTM D256
Notched Izod Impact (Area)	4.45	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	72.2	°C	ASTM D648

Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	126	°C	ASTM D1525
NOTE			
1.	51 mm/min		
2.	51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT