

Cellophane™ 350P

Regenerated Cellulose

Innovia Films Ltd.

Message:

Uncoated Permeable Films
Transparent film for applications where protection from moisture is not required
Literature reference: A200

General Information			
Features	Biodegradable		
	High Clarity		
	Renewable Resource Content		
Uses	Film		
	Industrial Applications		
Appearance	Clear/Transparent		
Forms	Film		
Films	Nominal Value	Unit	Test Method
Oxygen Transmission Rate (Wet) (24°C, 24 µm, 0.0% RH)	2.95	cm³/m²/24 hr	ASTM F1927
Film Gauge	24.4	µm	Internal Method
Yield (24.4 µm)	28.6	m²/kg	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

