

TUFNYL® RGF 25 HS BLACK

Polyamide 66

SRF Ltd.

Message:

Polyamide 66, 25% Glass fiber reinforced, heat stabilized, black pigmented material for injection molding

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.35	%	Internal Method
Water Absorption (Equilibrium)	0.50	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	90		
R-Scale	120		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	130	MPa	ISO 527-2
Tensile Strain (Break)	3.5	%	ISO 527-2
Flexural Modulus	7000	MPa	ISO 178
Flexural Stress	190	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	58.8	J/m	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	> 240	°C	ISO 75-2/B
1.8 MPa, Unannealed	> 210	°C	ISO 75-2/A
Melting Temperature	260	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	24	kV/mm	ASTM D149
Comparative Tracking Index	175 to 225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	80.0	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.20	%
Processing (Melt) Temp	240 to 350	°C
Mold Temperature	40.0 to 80.0	°C
Injection Pressure	3.50 to 12.5	MPa
Injection Rate	Fast	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT