

Bayfit® SA513 (95 Index)

Polyurethane

Covestro - PUR

Message:

Bayfit SA513 is a system for producing flexible polyurethane foam used as an acoustic countermeasure in various applications including carpet backing, dash insulators, etc. This foam is formulated to meet the necessary adhesive requirements between substrate materials and polyurethane foam, along with NAFTA OEM physical property specifications. This special formulation may be used with either open pour or closed pour mold filling techniques. Bayfit SA513 is available as a two-component polyurethane system from Bayer MaterialScience. As with any product, use of the Bayfit SA513 system in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

General Information			
Uses	Carpet backing Foam		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Density	0.0450	g/cm ³	ASTM D3574A
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	0.154	MPa	ASTM D3574D
Tensile Elongation ² (Break)	130	%	ASTM D3574E
Elastomers	Nominal Value	Unit	Test Method
Compression Set - 50%, Ct value	10	%	ASTM D3574D
Compression Deformation Stress - 40%	0.00460	MPa	ISO 3386
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components ³			
Component a	Mixing ratio by weight: 64		
Component B	Mixing ratio by weight: 100		
Additional Information	Nominal Value	Unit	Test Method
Part A Type: Isocyanate Appearance: Dark brown liquid Specific Gravity @ 25°C: 1.24 Viscosity @25°C: 23 to 24 MPa Part B Type: Polyol Appearance: Opaque liquid Specific Gravity @ 25°C: 1.02 Viscosity @25°C: 920 mPa-s Material Temperatures: 24 to 30°C Mold Temperature: 60 to 70°C Demold Time: 105 to 110 sec Mold Release Type: Solvent Based or Non-Solvent Based Reactivity (Machine Mix) at 25°C Cream Time: 11 to 14 sec Top of Cup: 19 to 21 sec String Gel: 30 to 33 sec Rise Time: 48 to 52 sec Free Rise Density: 2.0 to 2.35			
NOTE			
1.	Suffix T skin one side		

2.	Suffix T skin one side
3.	89 Index

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

