

Desmoderm® XP 2426

Polyurethane (Polyester based)

Covestro - PUR

Message:

Desmoderm XP 2426 is an aromatic one-component polyester urethane based on an aromatic diisocyanate.

General Information			
Features	Soft		
Uses	Footwear		
	Luggage		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Viscosity ¹			DIN EN ISO 3219/A.3
Tempered 5 hr, 120°C : 23°C	4.00 to 60.0	Pa·s	
Untempered : 23°C	4.00 to 20.0	Pa·s	
Light-Fastness	3.00		DIN EN ISO 105-B02
Softening Range	175 to 185	°C	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	100	µm	
Tensile Modulus - 100% (100 µm)	5.00 to 7.00	MPa	DIN 53504
Tensile Strength			DIN 53504
100 µm	45.0 to 55.0	MPa	
70°C, 100 µm ²	35.0 to 45.0	MPa	
Tensile Elongation (Break, 100 µm)	550 to 750	%	DIN 53504
NOTE			
1.	20% solution in dimethylformamide		
2.	after 14 days hydrolysis, 95% RH		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT