

LUVOCOM® 1800-8435

Polyethylene Terephthalate

LEHVOSS Group

Message:

LUVOCOM® 1800-8435 is a polyethylene terephthalate (PET) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM® The main features of 1800-8435 are:

Wear-resistant

Lubrication

Typical application areas include:

textile/fiber

engineering/industrial accessories

Automotive Industry

business/office supplies

General Information			
Additive	PTFE lubricant		
Features	Low friction coefficient		
	Good wear resistance		
	Lubrication		
Uses	Textile applications		
	Engineering accessories		
	Application in Automobile Field		
	Business equipment		
Appearance	Natural color		
Physical	Nominal Value	Unit	Test Method
Density	1.61	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (280°C/1.2 kg)	< 10.0	cm ³ /10min	ISO 1133
Molding Shrinkage	1.5 - 2.0	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2
Tensile Stress (Break)	35.0	MPa	ISO 527-2
Tensile Strain (Yield)	2.4	%	ISO 527-2
Flexural Modulus	1700	MPa	ISO 178
Flexural Stress	55.0	MPa	ISO 178
Flexural Strain at Flexural Strength	3.0	%	ISO 178
Maximum operating temperature-Short Term	180	°C	
Insulation Resistance	> 1.0E+12	ohms	IEC 60167
Impact	Nominal Value	Unit	Test Method

Charpy Unnotched Impact Strength (23°C)	15	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	100	°C	UL 746B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+12	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature			
Hot air dryer	120	°C	
Hot air dryer, B	80	°C	
Drying Time			
Hot air dryer	2.0 - 5.0	hr	
Hot air dryer, B	6.0 - 8.0	hr	
Rear Temperature	285 - 295	°C	
Middle Temperature	270 - 280	°C	
Front Temperature	265 - 275	°C	
Nozzle Temperature	265 - 275	°C	
Processing (Melt) Temp	280	°C	
Mold Temperature	60 - 120	°C	
Injection instructions			

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing the moisture level should not exceed 0.02%, otherwise molecular degradation and surface defects (e.g. smearing) may occur. As the material absorbs water very quickly, the predried material should be fed to the processing immediately. Processing temperatures above 300°C may very rapidly cause thermal damage and should therefore be avoided.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT