# Vipel® F701-RTP-13

### Polyester Alloy

AOC, L.L.C.

#### Message:

AOC's Vipel F701 Series resins are high molecular weight, two-stage isophthalic, unsaturated polyester resin with the wet out, cure and handling characteristics of general purpose resins.

They have an excellent shelf life and are ideal for filament winding and spray-up. A few selected resins are listed below including the high viscosity base resin, Vipel F701-FHG-00.

**BENEFITS** 

Corrosion resistance

General Information

AOC's Vipel F701 series resins provide excellent corrosion resistance when used in contact with inorganic and organic acids. Solvent resistance is field-proven for many petroleum products such as kerosene, heating oil and crude oils.

Refer to AOC's "Corrosion Resistant Resin Guide" for corrosion resistance information or for questions regarding suitability of a resin to any particular chemical environment contact AOC.

Versatile

Suitable for various fabricating methods such as hand lay-up, spray-up and filament winding.

Features	High molecular weight									
	m-benzene dimethyl  Solvent resistance  Good corrosion resistance  acid resistance									
						Oil resistance				
						Agency Ratings	FDA 21 CFR 177.2420			
	Forms	Liquid								
Processing Method	Filament power winding									
	Sprayable									
	Hand coating									
Physical	Nominal Value	Unit	Test Method							
Styrene Content	44	%								
Gel to Peak	13.0	min								
Peak Exotherm	188	°C								
Hardness	Nominal Value	Unit	Test Method							
Barcol Hardness	43		ASTM D2583							
Mechanical	Nominal Value	Unit	Test Method							
Tensile Modulus	3790	MPa	ASTM D638							
Tensile Strength										
. c. isiic sti ci igti	83.4	MPa	ASTM D638							
Tensile Elongation (Break)	2.8	MPa %	ASTM D638  ASTM D638							
Tensile Elongation (Break)	2.8	%	ASTM D638							
Tensile Elongation (Break) Flexural Modulus	2.8 4210	% MPa	ASTM D638 ASTM D790							

Deflection Temperature Under Load (1.8 MPa, Unannealed)	107	°C	ASTM D648
Uncured Properties	Nominal Value	Unit	
Density	1.08	g/cm³	
Viscosity (Brookfield LV)	0.15	Pa·s	
Gel Time	13	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

