

Kepamid® 1325M7

Polyamide 6

Korea Engineering Plastics Co., Ltd

Message:

Kepamid 1325M7 is a 25% mineral filled, reinforced polyamide-6.

Low warpage and good thermal properties.

It is applicable to automotive, electrical, electronic, and industrial parts.

General Information			
Filler / Reinforcement	Mineral,25% Filler by Weight		
Features	Low Warpage		
Uses	Automotive Applications		
	Electrical Parts		
	Electrical/Electronic Applications		
	Industrial Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	77.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.0	%	ASTM D638
Flexural Modulus (23°C)	5980	MPa	ASTM D790
Flexural Strength (23°C)	127	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	31	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	205	°C	
1.8 MPa, Unannealed	140	°C	
Melting Temperature	220	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Hopper Temperature	230 to 250	°C	
Rear Temperature	230 to 250	°C	

Middle Temperature	230 to 250	°C
Front Temperature	230 to 250	°C
Nozzle Temperature	230 to 250	°C
Mold Temperature	40.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

