

TAIRIPRO B8001

Polypropylene Impact Copolymer

Formosa Plastics Corporation

Message:

FCFC PP resin B8001 meets the certificates of FDA, RoHS and environmental protection.

General Information			
Features	Impact copolymer		
Agency Ratings	EC 1907/2006 (REACH)		
	FDA 21 CFR 177.1520		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Blow molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.30	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	1.5 - 1.9	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	26.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	> 200	%	ASTM D638
Flexural Modulus (23°C)	1080	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact			ASTM D256
-20°C, 3.18 mm	110	J/m	ASTM D256
23°C, 3.18 mm	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.35 mm)	105	°C	ASTM D648
Extrusion	Nominal Value	Unit	
Die Temperature	190 - 210	°C	
Extrusion instructions			
Screw Temp 200-230°C, Cooling water Temperature 30-50°C			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT