SPI HOPP12

Polypropylene Homopolymer

Service Polymers, Inc.

Message:

SPI HOPP12 is a Polypropylene Homopolymer (PP Homopolymer) product. It can be processed by injection molding and is available in North America. Applications of SPI HOPP12 include appliances, caps/lids/closures, consumer goods and household applications. Characteristics include: Low to No Odor/Taste Good Processability Good Stiffness High ESCR (Stress Crack Resistant) Homopolymer

General Information			
Features	Good Processability		
	Good Stiffness		
	High ESCR (Stress Crack Resist.)		
	High Isotactic		
	Homopolymer		
	Low to No Odor		
	Low to No Taste		
	Medium Viscosity		
Uses	Appliances		
	Closures		
	General Purpose		
	Household Goods		
	Toys		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, Injection Molded)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, Injection Molded)	33.1	MPa	ASTM D638
Tensile Elongation ² (Yield, Injection Molded)	8.0	%	ASTM D638
Flexural Modulus - 1% Secant ³ (Injection Molded)	1240	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection			
Molded)	32	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45			
MPa, Unannealed, Injection Molded)	100	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

