

Nypol® PA A3 T30 PRTA010 NR380

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Polyamide 6.6 with 30% mineral reinforced. Good set of thermal and mechanical properties. Ideal for injection molding.

General Information				
Filler / Reinforcement		Mineral,30% Filler by Weight		
Features		Good Electrical Properties		
Processing Method		Injection Molding		
Resin ID (ISO 1043)		>PA 6.6 MD30<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.34 to 1.37	--	g/cm ³	ISO 1183
Water Absorption (23°C, 24 hr)	1.1	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress	85.0	55.0	MPa	ISO 527-2
Tensile Strain (Break)	6.0	8.0	%	ISO 527-2
Flexural Modulus	6000	2600	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength (23°C, Injection Molded)	5.0	10	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	185	--	°C	ISO 75-2/Af
Melting Temperature	245 to 255	--	°C	ISO 11357-3
Injection	Dry	Unit		
Drying Temperature	80.0	°C		
Drying Time	4.0	hr		
Suggested Max Moisture	0.20	%		
Processing (Melt) Temp	250 to 275	°C		
Mold Temperature	60.0 to 80.0	°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

