

Mediprene® A2 500550M

Styrene Ethylene Butylene Styrene Block Copolymer

ELASTO

Message:

Overmoulding is a powerful technique that allows the production of finished parts in soft and hard material combinations without trimming or assembly. It offers many design and product advantages, allowing designers to differentiate products while meeting important user and patient demands, including soft-touch and cushioning for greater comfort and non-slip surfaces with improved grip for safety.

Special features

- Unfilled
- PVC, silicone & latex free
- 35 to 65 Shore A
- Medically approved raw materials
- Production site accredited to ISO 13485
- Sterilizable with gamma, EtO and steam
- Flexibility over broad temperature range
- Easy to colour
- Resistant to many fluids used in the health care environment
- Short cycle times
- Adhesion to a variety of substrates

The standard Mediprene® series bonds very well to polyolefins like polyethylene (PE) and polypropylene (PP). However, in several medical applications transparent engineering plastics like ABS, PC, PETG and SMMA (and their blends) are utilised. The Mediprene® A2 series has been developed to address demands for medical grade TPEs that bond well to these substrates.

Regulatory compliance

Representative Mediprene® grades have passed cytotoxicity tests according to ISO 10993-5 and are compliant with USP Class VI. Mediprene® TPE materials are PVC, silicone and latex free, making them allergen free and a viable alternative to PVC based compounds.

Applications

Potential applications for the Mediprene® A series include; seals, membranes, closures, friction grips, soft-touch handles. Mediprene® TPEs provide enhanced sealing capabilities in fluid environments.

General Information	
Features	Bondability
	Ethylene Oxide Sterilizable
	Fast Molding Cycle
	Good Abrasion Resistance
	Good Colorability
	Good Flexibility
	Radiation Sterilizable
	Soft
	Steam Sterilizable
Uses	Bonding
	Closures
	Flexible Grips
	Handles
	Medical/Healthcare Applications
	Membranes
	Overmolding
	Seals

Agency Ratings	ISO 10993 Part 5 USP Class VI		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Coextrusion Extrusion Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.970	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/10.0 kg)	7.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 4.00 mm, Injection Molded)	55		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	5.00	MPa	
100% Strain	2.00	MPa	
300% Strain	3.50	MPa	
Tensile Elongation (Break)	500	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	24.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Service Temperature ¹	-50 to 125	°C	
Peel Force ² (2.50 mm)	5.0	kN/m	ASTM D903
Injection	Nominal Value	Unit	
Rear Temperature	210 to 250	°C	
Middle Temperature	210 to 250	°C	
Front Temperature	210 to 250	°C	
Mold Temperature	30.0 to 60.0	°C	
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	210 to 250	°C	
Cylinder Zone 2 Temp.	210 to 250	°C	
Cylinder Zone 3 Temp.	210 to 250	°C	
Cylinder Zone 4 Temp.	210 to 250	°C	
Cylinder Zone 5 Temp.	210 to 250	°C	
NOTE			
1.	unstressed material		

2.

90° peel tests conducted at 100 mm/min with Mediprene® A2 grade (2.5 mm thickness, 25 mm width) overmoulded onto ABS (Terlux 2802HD).

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

