SABIC® FORTIFY™ C0560D

Thermoplastic Polyolefin Elastomer

Saudi Basic Industries Corporation (SABIC)

Message:

General Information

SABIC® FORTIFY™ C0560D is an ethylene octene copolymer. This product is available as free flowing pellets.

SABIC® FORTIFY™ C0560D is designed as a low density and high performance copolymer modifier to provide superior impact properties and flow characteristics

Typical applications are impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

Please take notice of specific storage and handling conditions.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General information				
Features	Low density			
	Copolymer			
	Impact resistance, good			
	Good liquidity			
	Octene comonomer			
Uses	Wire and cable applications			
	Composite			
	Plastic modification			
	Footwear			
Forms	Particle			
Processing Method	Wire & Cable Extrusion			
	Compound extrusion			
Physical	Nominal Value	Unit	Test Method	
Density	0.863	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	0.50	g/10 min	ASTM D1238	
Mooney Viscosity (ML 1+4, 121°C)	36	MU	ASTM D1646	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness			ASTM D2240	
Shaw A, 1 sec	64		ASTM D2240	
Shaw D, 1 sec	17		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Modulus - 100% Secant	1.90	MPa	ASTM D638	
Tensile Strength (Break)	6.10	MPa	ASTM D638	
Tensile Elongation (Break)	> 1000	%	ASTM D638	
Flexural Modulus - 1% Secant	8.80	MPa	ASTM D790	

Tear Strength ¹	33.3	kN/m	ASTM D624	
Thermal	Nominal Value	Unit	Test Method	
Glass Transition Temperature	-56.0	°C	Internal method	
Melting Temperature	45.0	°C	Internal method	
Additional Information				
All physical properties were measured on compression molded specimens.				
NOTE				
1.	C mould			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

