

Propafilm™ GLS100

Polypropylene Alloy

Innovia Films Ltd.

Message:

High Speed Overwrapping Film with Shrink Tightening Properties

Biaxially oriented polypropylene (BOPP) film co-extruded on both sides with heat sealable polyolefinic copolymers.

GLS80/100 are suitable for use in the tobacco industry for both high speed and display outers where exceptional pack appearance and wrap tightness are required.

General Information			
Features	Flavor & Aroma Barrier		
	Food Contact Acceptable		
	Heat Sealable		
	Moisture Barrier		
	Pleasing Surface Appearance		
	Slip		
	Solvent Resistant		
Uses	Packaging		
	Shrink Wrap		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Film		
Processing Method	Coextrusion		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage			Internal Method
Flow : 80°C, 1 min	3.7	%	
Flow : 120°C, 1 min	7.0	%	
Across Flow : 80°C, 1 min	3.5	%	
Across Flow : 120°C, 1 min	11	%	
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic, Outside/Outside	0.25		
vs. Itself - Static, Outside/Outside	0.40		
Films	Nominal Value	Unit	Test Method
Secant Modulus ¹			ASTM D882
1% Secant, MD	3000	MPa	
1% Secant, TD	3600	MPa	
Tensile Strength ²			ASTM D882
MD : Yield	170	MPa	
TD : Yield	210	MPa	

Tensile Elongation ³			ASTM D882
MD : Break	120	%	
TD : Break	80	%	
Seal Strength ⁴	0.19	N/mm	Internal Method
Seal Initiation Temperature ⁵	116 to 141	°C	Internal Method
Oxygen Permeability (23°C, 0% RH)	35	cm ³ ·mm/m ² /atm/24 hr	ASTM F1927
Water Vapor Transmission Rate			ASTM F1770
23°C, 85% RH	0.78	g/m ² /24 hr	
38°C, 90% RH	4.0	g/m ² /24 hr	
Film Gauge	100		Internal Method
Yield	44.0	m ² /kg	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (20°)	140		ASTM D2457
Haze ⁶	1.0	%	ASTM D1003
NOTE			
1.	10%/min		
2.	50%/min		
3.	50%/min		
4.	225°F; 1sec; 15lb/in ²		
5.	2secs; 15psi		
6.	Wide angle; 2.5°		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT