

LUVOTECH® GS 58

Polyamide 66

Lehmann & Voss & Co.

Message:

LUVOTECH®GS 58 is a polyamide 66 (nylon 66) material that contains a fiberglass reinforcement. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOTECH®The main features of GS 58 are:

Good dimensional stability

Wear-resistant

Lubrication

Typical application areas include:

engineering/industrial accessories

Electrical/electronic applications

textile/fiber

Automotive Industry

business/office supplies

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Additive	Lubricant		
Features	Good dimensional stability		
	Low friction coefficient		
	Good wear resistance		
	Lubrication		
Uses	Gear		
	Textile applications		
	Engineering accessories		
	Switch		
	Application in Automobile Field		
	Business equipment		
Appearance	Dark gray		
Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm ³	ISO 1183
Molding Shrinkage	0.20 - 0.50	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13500	MPa	ISO 527-2
Tensile Stress (Break)	250	MPa	ISO 527-2
Tensile Strain (Yield)	3.0	%	ISO 527-2
Flexural Modulus	12000	MPa	ISO 178
Flexural Stress	320	MPa	ISO 178

Coefficient of Friction			
Dynamic	0.33		
Static	0.26		
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	95	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	100	°C	UL 746B
Maximum operating temperature-Short Term	140	°C	
Insulation Resistance	> 1.0E+12	ohms	IEC 60167
Vicat Softening Temperature	250	°C	ISO 306/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+12	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature			
Hot air dryer, A	75.0	°C	
Vacuum dryer, B	105	°C	
Drying Time			
Hot air dryer, A	6.0 - 16	hr	
Vacuum dryer, B	4.0 - 6.0	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	290 - 310	°C	
Middle Temperature	290 - 310	°C	
Front Temperature	290 - 310	°C	
Nozzle Temperature	280 - 300	°C	
Processing (Melt) Temp	290	°C	
Mold Temperature	90.0 - 120	°C	
Injection instructions			
General			
In general LUVOTECH® can be processed on conventional injection moulding machines while observing the usual technical guidelines.			
Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.			
Lengthy dwell times for the melts in the cylinder should be avoided.			
Lower the temperatures during interruptions!			
Predrying (optional)			
It is advisable to predry the granulate with a suitable dryer immediately before processing.			
The granulate may absorb moisture from the air.			
Delivery Form & Storage			
Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.			
Preferably storage should be effected in dry and normally temperatured rooms			
Additional Information			
During processing the moisture level should not exceed 0.1%, otherwise molecular degradation and surface defects (e.g. smearing) may occur. Due to rapid absorption of water, originally sealed containers should only be opened immediately prior to processing. Excessively high predrying temperatures may cause discoloration.			
The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.			
Please contact us for further information.			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

