

# Hanwha Total PP GH43

High Crystallinity Polypropylene

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

## Message:

GH43 is a G/F modified polypropylene compound modified by glass fiber filling to improve mechanical rigidity and heat-resistance. It is produced by modifying a variety of base PPs, including HIPP (High Isotactic Polypropylene), with Hanwha's special processing technology. Its excellent quality makes it ideal for use in air conditioner fans and automobile cooling fans; and like products requiring high rigidity and high impact-resistance.

General Information			
UL YellowCard	E140331-222929		
Filler / Reinforcement	Glass fiber reinforced material		
Features	Good dimensional stability		
	Low warpage		
	Rigidity, high		
	High tensile strength		
	High strength		
	m-benzene dimethyl		
	Impact resistance, high		
	Workability, good		
	High liquidity		
	Heat resistance, high		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Electrical components		
	Electrical appliances		
	Power/other tools		
	Industrial application		
	Mixing		
	Household goods		
	Application in Automobile Field		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (2.00 mm)	0.20 - 0.90	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>	108	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	3.0	%	ASTM D638
Apparent Bending Modulus	147	MPa	ASTM D747
Flexural Modulus <sup>3</sup>	5880	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	163	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	180 - 220	°C	
Middle Temperature	180 - 220	°C	
Front Temperature	180 - 220	°C	
Mold Temperature	50.0 - 80.0	°C	
Injection Pressure	49.0 - 88.3	MPa	
Back Pressure	0.490 - 0.981	MPa	
Screw Speed	30 - 80	rpm	
Injection instructions			
Injection Speed: max			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	5.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

