

Plenco 06527 (Transfer)

Phenolic

Plastics Engineering Co.

Message:

PLENCO 06527 is a woodflour and mineral filled resole phenolic molding compound. It is available in brown.

General Information			
Filler / Reinforcement	Mineral filler		
	Wood flour		
Appearance	Brown		
Forms	Particles		
Processing Method	Resin transfer molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.57	g/cm ³	ASTM D792
Apparent Density	0.59	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	0.27	%	ASTM D955
Water Absorption (24 hr)	0.35	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (E-Scale)	56		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10600	MPa	ASTM D638
Tensile Strength	52.0	MPa	ASTM D638
Tensile Elongation (Break)	0.80	%	ASTM D638
Flexural Modulus	8450	MPa	ASTM D790
Flexural Strength	82.7	MPa	ASTM D790
Compressive Strength	143	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	24.3	J/m	ASTM D256
Notched Izod Impact	26	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	216	°C	ASTM D648
Continuous Use Temperature	188	°C	ASTM D794
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.2E+12	ohms · cm	ASTM D257
Dielectric Strength ¹	9.3	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	6.30		ASTM D150
Dissipation Factor (1 MHz)	0.069		ASTM D150
Arc Resistance	162	sec	ASTM D495

Comparative Tracking Index (CTI)	175	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	34	%	ASTM D2863
Additional Information			
The value listed as Comparative Tracking Index, UL 746 was tested according to ASTM D3638.The value listed as Mold Shrink, Linear-Flow, ASTM D955 was tested according to the ASTM D6289 standard.Post Shrinkage, ASTM D6289, 72hr, 120°C: 0.26%Drop Ball Impact, PLENCO Method: 157 J/m			
Injection	Nominal Value	Unit	
Mold Temperature	165 - 182	°C	
Back Pressure	0.300	MPa	
Screw Speed	< 60	rpm	
Injection instructions			
Transfer Time: 3-8 secTransfer Pressure: 5.5-6.9 MPaPreheating Temperature: 104-115°C			
NOTE			
1.	Method A (short time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT