

Vyncolit® 4523XB

Phenolic

Vyncolit N.V.

Message:

Vyncolit® 4523XB is an organic and inorganic filled phenolic molding compound with improved heat resistance compared to organic filled compounds.

General Information			
Filler / Reinforcement	Organic filler		
Appearance	Black		
Forms	Particle		
Processing Method	Resin transfer molding		
	Compression molding		
	Injection molding		
Resin ID (ISO 1043)	>PF-(MD+L1D)55		
Physical	Nominal Value	Unit	Test Method
Density	1.61	g/cm³	ISO 1183
Apparent Density	0.71	g/cm³	ISO 60
Molding Shrinkage - Flow	0.63	%	ISO 2577
Water Absorption (23°C, 24 hr)	0.17	%	ISO 62
Post Shrinkage	0.19	%	ISO 2577
Flexural Strain at Break	1.6	%	ISO 178
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	10000	MPa	ISO 527-2
Tensile Stress (Break, Injection Molded)	55.0	MPa	ISO 527-2
Tensile Strain (Break, Injection Molded)	0.93	%	ISO 527-2
Flexural Modulus (Injection Molded)	9000	MPa	ISO 178
Flexural Stress (Injection Molded)	106	MPa	ISO 178
Compressive Stress	210	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (Injection Molded)	1.9	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (Injection Molded)	8.5	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	176	°C	ISO 75-2/Af
Linear thermal expansion coefficient			TMA
Flow	2.9E-5	cm/cm/°C	TMA
Lateral	4.8E-5	cm/cm/°C	TMA
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	7.4E+12	ohms	IEC 60093
Volume Resistivity	2.7E+14	ohms·cm	IEC 60093
Dielectric Strength	34	kV/mm	IEC 60243-1
Comparative Tracking Index	175	V	IEC 60112
Injection	Nominal Value	Unit	
Rear Temperature	60.0	°C	
Middle Temperature	73.9	°C	
Nozzle Temperature	87.8	°C	
Processing (Melt) Temp	98.9 - 116	°C	
Mold Temperature	166 - 188	°C	
Injection Pressure	100 - 248	MPa	
Holding Pressure	30.0 - 89.6	MPa	
Back Pressure	4.83 - 15.2	MPa	
Injection instructions			

Plastication: 50rpmInjection Time: 2 to 8 secHold Time: 1 to 5 sec/mmCure Time, 0.125 in: 5 to 12 sec/mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

