# AZR-Ecoplast 143 HDPE grey 0.35

## High Density Polyethylene

#### UrbanPlast SIA

### Message:

AZR Ecoplast 143 HDPE grey 0.35 is high impact resistance in - extruder made thermoplastic polyethylene with a low temperature plastic composite profile for injection molding.

AZR Ecoplast 143 HDPE grey 0.35 is controlled technology extra high impact resistance thermoplastic polyethylene with rheological properties even at low temperatures.

#### Applications:

AZR Ecoplast 143 HDPE grey 0.35 is designed to offer excellent stiffness, low warping, good/acceptable toughness, plasticity and good moldability (extrudability). This resin is ideally suited for injection molded crates, cases, trays, tote, containers, bins and other objects requiring high rigidity. Food Contact:

AZR Ecoplast 143 HDPE grey 0.35 complies with EU directive 10/2011.

| General Information |                                   |      |             |  |  |
|---------------------|-----------------------------------|------|-------------|--|--|
| Recycled Content    | Yes                               |      |             |  |  |
| Features            | Controlled Rheology               |      |             |  |  |
|                     | Food Contact Acceptable           |      |             |  |  |
|                     | Good Moldability                  |      |             |  |  |
|                     | Good Toughness                    |      |             |  |  |
|                     | High Rigidity                     |      |             |  |  |
|                     | High Stiffness                    |      |             |  |  |
|                     | Low Temperature Impact Resistance |      |             |  |  |
|                     | Low Warpage                       |      |             |  |  |
|                     | Recyclable Material               |      |             |  |  |
|                     | Ultra High Impact Resista         | nce  |             |  |  |
|                     |                                   |      |             |  |  |
| Uses                | Containers                        |      |             |  |  |
|                     | Crates                            |      |             |  |  |
|                     | Rigid Packaging                   |      |             |  |  |
| Agency Ratings      | EU 10/2011                        |      |             |  |  |
|                     | EU No 10/2011                     |      |             |  |  |
|                     |                                   |      |             |  |  |
| Appearance          | Grey                              |      |             |  |  |
| Processing Method   | Extrusion                         |      |             |  |  |
|                     | Injection Molding                 |      |             |  |  |
| Physical            | Nominal Value                     | Unit | Test Method |  |  |

| Physical                  | Nominal Value | Unit     | Test Method |
|---------------------------|---------------|----------|-------------|
| Density                   | 0.970         | g/cm³    | ISO 1183    |
| Apparent Density          | 0.55          | g/cm³    | ISO 60      |
| Melt Mass-Flow Rate (MFR) |               |          | ISO 1133    |
| 190°C/2.16 kg             | 0.19 to 0.39  | g/10 min |             |

| 190°C/5.0 kg                     | 1.1 to 1.4    | g/10 min |                 |
|----------------------------------|---------------|----------|-----------------|
| Humidity - External <sup>1</sup> | 0.20 to 0.40  | %        | Internal Method |
| Charpy Impact Strength           | 200           | J/m      | ISO 148         |
| Odor - 15 estimators             | 1.00          | points   | EN 13752        |
| Hardness                         | Nominal Value | Unit     | Test Method     |
| Durometer Hardness               |               |          | ASTM D2240      |
| Shore A                          | 97            |          |                 |
| Shore D                          | 65            |          |                 |
| Mechanical                       | Nominal Value | Unit     | Test Method     |
| Tensile Modulus                  | > 1690        | МРа      | ISO 527-2       |
| Tensile Stress (Break)           | > 24.0        | MPa      | ISO 527-2       |
| Tensile Strain (Break)           | > 34          | %        | ISO 527-2       |
| Injection                        | Nominal Value | Unit     |                 |
| Processing (Melt) Temp           | 180 to 190    | °C       |                 |
| NOTE                             |               |          |                 |

1. Nexis fiber method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

