

Silopren® LSR 2670

Silicone Rubber, LSR

Momentive Performance Materials Inc.

Message:

Silopren LSR 2670 is a two-component liquid silicone rubber for injection molding processes. In comparison to Silopren LSR 2070, Silopren LSR 2670 shows a lower viscosity, improved tear resistance and a higher reactivity. Therefore, it is also possible to reduce the vulcanization temperature while maintaining a standard crosslinking rate. The increased reactivity does not affect the properties of the vulcanizate.

Key Features and Benefits

Vulcanizates of Silopren LSR 2670 are typically distinguished by the following properties:

- High reactivity, lower viscosity, shorter cycle time
- Excellent thermal stability
- Biocompatible
- Sterilizable with ethylene oxide, steam and gamma radiation
- High stability and flexibility at low temperatures
- Good rubber-like properties, high tear resistance
- Long service life at dynamic stress
- High stability to ozone and ultraviolet light
- Outstanding resistance to aging
- Excellent dielectric behavior over a wide range of temperatures
- Not readily combustible, does not melt or drip
- Easily pigmentable with LSR color pastes
- KTW approved

Potential Applications

Because of its outstanding properties, Silopren LSR 2670 is an excellent candidate to consider for the following elastomeric articles:

- Sealing elements
- O-rings
- Stoppers
- Keypads
- Vibration dampers
- Pressure cookers parts
- Spark plug boots, catheters, parts of medical technical equipment s.o.

General Information	
Features	Biocompatible
	Ethylene Oxide Sterilizable
	Good Colorability
	Good Stability
	Good Tear Strength
	Good Thermal Stability
	Good UV Resistance
	High Reactivity
	Low Temperature Flexibility
	Ozone Resistant
	Radiation Sterilizable
	Steam Sterilizable
	Vibration Damping
Uses	Medical/Healthcare Applications
	Seals

Agency Ratings	BfR Food Contact, Unspecified Rating		
	DVGW W270		
	FDA 21 CFR 177.2600		
	ISO 10993		
	KTW Unspecified Rating		
	USP Class VI		
	WRAS Unspecified Rating		
Forms	Liquid		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	DIN 53479
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	69		DIN 53505
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	9.50	MPa	DIN 53504
Tensile Elongation (Break)	350	%	DIN 53504
Tear Strength ¹	30.0	kN/m	ASTM D624
Compression Set (175°C, 22 hr)	20	%	ISO 815
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Part A	Mix Ratio by Weight: 1.0		
Part B	Mix Ratio by Weight: 1.0		
Post Cure Time (200°C)	4.0	hr	
Additional Information	Nominal Value	Unit	Test Method
Vulcanization (175°C)	10.0	min	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
-- ²	Translucent		
-- ³	Translucent		
Viscosity			DIN 53018
20°C ⁴	550	Pa · s	
20°C ⁵	550	Pa · s	
Pot Life (20°C)	4300	min	
NOTE			
1.	Die B		
2.	Part B		
3.	Part A		
4.	Part B		
5.	Part A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

