

# Eltex® MED PH22D630

Low Density Polyethylene

INEOS Olefins & Polymers Europe

## Message:

Low Density Polyethylene for Pharmaceutical Blow Moulding

### Benefits & Features

Eltex® MED PH22D630 is a LD-polyethylene produced in a high-pressure process intended for blow moulding of soft and flexible packages for pharmaceutical products.

Eltex® MED PH22D630 is produced according to good manufacturing practice and is additive-free.

Eltex® MED PH22D630 is available in granular form.

### Applications

Eltex® MED PH22D630 can be used in “blow-fill and seal” machines for the production ampoules and bottles. The product can also be used for pharmaceutical products manufactured with other conversion techniques such as injection moulding and film blowing. The product is not intended for heat sterilisation

General Information			
Features	Additive Free		
	Good Flexibility		
	Low Density		
	Soft		
Uses	Bottles		
	Pharmaceutical Packaging		
Agency Ratings	EP Monograph 3.1.4		
	USP 29		
	USP Class VI		
RoHS Compliance	Contact Manufacturer		
Forms	Granules		
Processing Method	Blow Molding		
	Blown Film		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.30	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	49		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	240	MPa	ISO 527-2/1
Tensile Stress (Yield)	10.0	MPa	ISO 527-2/50

Tensile Strain (Break)	450	%	ISO 527-2/50
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	49.0	°C	ISO 75-2/B
Extrusion	Nominal Value	Unit	
Melt Temperature	160 to 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

