

Jam PE 02X02

Very Low Density Polyethylene

Jam Petrochemical Company

Message:

Jam PE 02X02 is a Very Low Density Polyethylene product. It can be processed by blown film and is available in Africa & Middle East. Applications of Jam PE 02X02 include fabrics/fibers, film and membranes.

General Information			
Uses	Film		
	Geo Membranes		
	Monofilaments		
	Netting		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.902 to 0.904	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.8	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
Dart Drop Impact (25 µm, Blown Film)	250	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm, Blown Film	230	g	
TD : 25 µm, Blown Film	300	g	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	67.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 µm, Blown Film)	26		ASTM D1790
Haze (25.0 µm, Blown Film)	30	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT