

# TyrFil® G-2

Polyurethane (MDI)  
Pathway Polymers

Message:

TyrFil® G-2 is a Polyurethane (MDI) (PUR-MDI) material. It is available in North America.

General Information		
Uses	Tire Repair	
Appearance	Brown	
Forms	Liquid	
Hardness	Nominal Value	
Durometer Hardness (Shore A)	26 to 30	
Elastomers	Nominal Value	Unit
Tensile Strength (Break)	1.82	MPa
Tensile Elongation (Break)	350	%
Tear Strength		
-- 1	6.65	kN/m
Split	0.70	kN/m
Bayshore Resilience	65	%
Fill Analysis	Nominal Value	Unit
Melt Density		
25°C 2	1.08	g/cm³
25°C 3	1.05	g/cm³
NOTE		
1.	Die C	
2.	Prepolymer (side B)	
3.	Catalyst (side A)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT