

Formolene® 4101M

Polypropylene Homopolymer
Formosa Plastics Corporation, U.S.A.

Message:

Formolene® 4101M is polypropylene homopolymer designed for staple fiber applications. It contains a unique combination of stabilizers and additives, which provides excellent processability and good end use performance. It provides excellent resistance to gas fading.
Formolene® 4101M meets all requirements of the U. S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact.

General Information			
Additive	Unspecified Additive		
	Unspecified Stabilizer		
Features	Food Contact Acceptable		
	Gas-fading Resistant		
	Good Processability		
	Good Stability		
	Homopolymer		
Uses	Staple Fibers		
Agency Ratings	EC 1907/2006 (REACH)		
	FDA 21 CFR 177.1520		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	8.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, Injection Molded)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, Injection Molded)	33.8	MPa	ASTM D638
Tensile Elongation ² (Yield, Injection Molded)	9.0	%	ASTM D638
Flexural Modulus - 1% Secant ³ (Injection Molded)	1240	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	32	J/m	ASTM D256
NOTE			
1.	50 mm/min		
2.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

