Novalloy-A A2706

Acrylonitrile Butadiene Styrene + Nylon

PlastxWorld Inc.

Message:

Novalloy-A A2706 is an Acrylonitrile Butadiene Styrene + Nylon (ABS+Nylon) product filled with 30% glass fiber. It is available in Europe. Characteristics include:

Flame Rated

Heat Resistant

High Strength

Impact Resistant

Flammability

Flame Rating (1.50 mm)

Dry

ΗВ

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		High Heat Resistance		
		High Impact Resistance		
		High Tensile Strength		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.31		g/cm³	ASTM D792
Molding Shrinkage - Flow	0.10 to 0.50		%	ASTM D955
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness	117			ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (Break)	124	117	MPa	ASTM D638
Tensile Elongation (Break)	4.0	5.0	%	ASTM D638
Flexural Modulus	6890	5650	MPa	ASTM D790
Flexural Strength	207	165	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
		160	J/m	
23°C, 3.18 mm	140		J/m	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature				
Under Load (1.8 MPa, Unannealed)	200	195	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Conditioned

Test Method

UL 94

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

