

Hifax CB 1160 G1

Polypropylene Copolymer
LyondellBasell Industries

Message:

"Hifax" CB 1160 G1 is a medium flow, 10% mineral filled high impact polypropylene copolymer suitable for injection moulding. The grade has been specifically designed for moulding large complex parts that require high impact strength as well as good stiffness. This product is designed for outdoor applications such as bumpers. This grade is available in custom colour, pellet form.

General Information			
Filler / Reinforcement	Mineral,10% Filler by Weight		
Features	Copolymer		
	Good Stiffness		
	Good Surface Finish		
	High Impact Resistance		
	Medium Flow		
	Non-Toxic		
	UV Absorbing		
Uses	Automotive Applications		
	Automotive Bumper		
	Automotive Exterior Parts		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	14	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	19.0	MPa	ISO 527-2
Flexural Modulus	1400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	6.5	kJ/m ²	
23°C	46	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	50.0	°C	ISO 75-2/A
Vicat Softening Temperature	52.0	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

