

Tecodur® PB70 GR30 NL100 HT01

Polybutylene Terephthalate + PET

Eurotec Engineering Plastics

Message:

PBT/PET, 30% glass fiber reinforced, high heat stabilized, natural

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	(PBT+PET) GF30		
Physical	Nominal Value	Unit	Test Method
Density	1.55	g/cm³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	0.10	%	ISO 62
Moisture Content	< 0.080	%	ISO 15512
Back Pressure	Low		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	10000	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	140	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	8.0	kJ/m²	
23°C	9.0	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	195	°C	ISO 75-2/A
Melting Temperature ¹	225 to 255	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	HB		

1.60 mm	HB	
Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	4.0 to 6.0	hr
Hopper Temperature	50.0 to 70.0	°C
Processing (Melt) Temp	260 to 280	°C
Mold Temperature	60.0 to 110	°C
Injection Rate	Fast	
Holding Pressure	40.0 to 80.0	MPa
NOTE		
1.	10 K/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

