

Bergadur™ IDES 243031

Polybutylene Terephthalate

PolyOne Corporation

Message:

Bergadur™IDES 243031 is a polybutene terephthalate (PBT) product, which contains a filler of 20% glass fiber reinforcement. It can be processed by injection molding and is available in the Asia-Pacific region. The main characteristics are: flame retardant/rated flame.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 - 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	115	MPa	ASTM D638
Flexural Modulus ²	6000	MPa	ASTM D790
Flexural Strength ³	185	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	90	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	195	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Charge Decay Time - 12% RH, 5000 kV to 50 kV	277777774164.2	hr	MIL B-81705C
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110 - 130	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	240 - 270	°C	
Middle Temperature	240 - 270	°C	
Front Temperature	240 - 270	°C	
Mold Temperature	75.0 - 95.0	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	5.0 mm/min		
2.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

