

Niblan F30 AE/V0

Polybutylene Terephthalate

Soredi S.p.a.

Message:

PBT 20% glass fibre reinforced, flame retardant UL officially certified by Underwriter Laboratories (yellow card) as per UL 94 V0 at 1.6 mm rating.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Flame Retardant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.70	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus ¹	10000	MPa	ASTM D790
Flexural Strength ² (Break)	180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	215	°C	ASTM D648
Peak Crystallization Temperature (DSC)	220	°C	ASTM D3418
CLTE - Flow (23 to 55°C)	2.5E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Ignition Temperature (2.00 mm)	960	°C	IEC 60695-2-13
NOTE			
1.	1.3 mm/min		
2.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

