

EcoLon® 2020-BK2

Polyamide 6

Wellman Engineering Resins

Message:

EcoLon® 2020-BK2 is a Polyamide 6 (Nylon 6) material filled with 40% glass\mineral. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding. Primary attribute of EcoLon® 2020-BK2: Eco-Friendly/Green.

Typical application of EcoLon® 2020-BK2: Automotive

General Information			
Filler / Reinforcement	Glass\Mineral,40% Filler by Weight		
Recycled Content	Yes		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	0.70 to 1.1	%	
Flow : 23°C	0.20 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	105	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	2.0	%	ISO 527-2
Flexural Modulus (23°C)	8700	MPa	ISO 178
Flexural Stress (23°C)	165	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	6.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	200	°C	ISO 75-2/A
Melting Temperature (DSC)	220	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	277 to 293	°C	
Middle Temperature	271 to 282	°C	
Front Temperature	266 to 277	°C	
Nozzle Temperature	254 to 282	°C	
Processing (Melt) Temp	271 to 299	°C	
Mold Temperature	71.1 to 93.3	°C	
Injection Pressure	34.5 to 138	MPa	
Back Pressure	0.345	MPa	

Screw Speed

30 to 120

rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

