INEOS PP 200-GA02

Polypropylene Random Copolymer

INEOS Olefins & Polymers Europe

Message:

200-GA02 is a general purpose random copolymer intended for extrusion applications requiring low melt flow and good melt strength. Applications Sheet extrusion for stationery applications Thermoforming Benefits and Features Improved processability Low stress whitening under bending Excellent colour and temperature stability

| General Information | | | |
|---------------------|------------------------|------|-------------|
| Features | General Purpose | | |
| | Good Color Stability | | |
| | Good Melt Strength | | |
| | Good Processability | | |
| | Good Thermal Stability | | |
| | Low Flow | | |
| | Random Copolymer | | |
| | | | |
| Uses | General Purpose | | |
| | Sheet | | |
| | Stationary Supplies | | |
| | | | |
| RoHS Compliance | Contact Manufacturer | | |
| Forms | Pellets | | |
| Processing Method | Sheet Extrusion | | |
| | Thermoforming | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |

| Physical | Nominal Value | Unit | Test Method |
|--|---------------|----------|-------------|
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 2.0 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Yield) | 27.0 | MPa | ISO 527-2 |
| Flexural Modulus (23°C) | 950 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact Strength (23°C) | 10 | kJ/m² | ISO 180/1A |
| Thermal | Nominal Value | Unit | Test Method |
| Peak Melting Temperature | 149 | °C | ASTM D3417 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

