

TEREZ PA 6.6/6 7650 TD/1

Polyamide 66/6 Copolymer

TER HELL PLASTIC GMBH

Message:

Standard type with medium viscosity Polyamid 66/6 Blend with dry impact resistant modification
For all kind of injection molding parts

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
	Medium Viscosity		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2
Tensile Strain (Yield)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	75.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	175	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT