

RTP 2740 U-80A

Styrene Butadiene Styrene Block Copolymer

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
-Preliminary Product Data per RTP Co.-

General Information			
RoHS Compliance	Contact Manufacturer		
Appearance	Black Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.7	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.050	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	8.27	MPa	ASTM D638
Tensile Elongation (Break)	410	%	ASTM D638
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Rear Temperature	149 to 199	°C	
Middle Temperature	149 to 199	°C	
Front Temperature	149 to 199	°C	
Mold Temperature	10.0 to 40.6	°C	
Injection Pressure	3.45 to 6.89	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

