Carbotex KG-10MRA

Polycarbonate

Kotec Corporation

Message:

Carbotex KG-10MRA is a Polycarbonate (PC) product filled with 10% glass fiber. It is available in Africa & Middle East, Europe, Latin America, or North America

Characteristics include:

Flame Rated

Good Mold Release

High Viscosity

Mold Release Agent

General Information			
UL YellowCard	E146413-223408		
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
Additive	Mold Release		
Features	Good Mold Release		
	High Viscosity		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	< 0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	74.0	МРа	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	3530	MPa	ASTM D790
Flexural Strength	118	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	70	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	140	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (1.60 mm)	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.20		ASTM D150
Dissipation Factor (1 MHz)	8.0E-3		ASTM D150
Arc Resistance	110	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method

Flame Rating (3.00 mm)	V-0	UL 94
Optical	Nominal Value	Test Method
Haze (3.00 mm)	Translucent	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

