Kynar® 760

Polyvinylidene Fluoride

Arkema

Message:

KYNAR® 760 is a semi-crystalline high molecular weight pelletized polymer of vinylidene fluoride. It is a versatile engineering plastic with an outstanding balance of physical and chemical properties which qualify it for high performance service in a wide range of applications. It is a thermoplastic fluoropolymer capable of being fabricated in standard processing equipment. The molecular weight and molecular weight distribution have been carefully tailored to supply a grade suitable for a variety of processing requirements and end-use applications.

KYNAR® 760 is suitable for the compression molding of block and extrusion of thick monofilaments and pipe.

The powder form of this resin grade is available as KYNAR® 761 PVDF.

General Information			
UL YellowCard	E54699-636464		
Features	High Molecular Weight		
	Semi Crystalline		
Uses	Filaments		
	Piping		
Forms	Pellets		
Processing Method	Compression Molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.77 to 1.79	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	76 to 80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	44.8 to 55.2	MPa	

•		J.	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	76 to 80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	44.8 to 55.2	MPa	
Break, 23°C	34.5 to 55.2	MPa	
Tensile Elongation (Break, 23°C)	20 to 100	%	ASTM D638
Flexural Modulus (23°C)	1380 to 2310	MPa	ASTM D790
Flexural Strength (23°C)	58.6 to 75.8	MPa	ASTM D790
Compressive Strength (23°C)	68.9 to 103	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	165 to 172	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ¹ (20°C)	2.0E+14	ohms·cm	ASTM D257
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (232°C, 100 sec^-1)	2300 to 2900	Pa·s	ASTM D3835
NOTE			

1. 65% R.H.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

