

Generic Nylon 11 - Unspecified

Polyamide 11

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Nylon 11 - Unspecified
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Filler		
Physical	Nominal Value	Unit	Test Method
Density	1080	kg/m ³	ISO 1183 ¹
Water Absorption (Saturation)	1.6	%	ISO 62 ²
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature (50°C/h, B (50N))	165	°C	ISO 306 ³
Melting Temperature ⁴	187	°C	ISO 11357-3 ⁵
NOTE			

1.

Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

2.

Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

3.

Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

4.

10 °C/min

5.

Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT