

Kingfa JH710 G10D

Polycarbonate Alloy

Kingfa

Message:

Kingfa JH710 G10D is a polycarbonate alloy (PC alloy) material, which contains a 10% glass fiber reinforced material. This product is available in North America or Asia Pacific region. The processing method is injection molding.

The main characteristics of Kingfa JH710 G10D are:

flame retardant/rated flame

Flame Retardant

high strength

beautiful

Typical application areas include:

Electrical/electronic applications

printing applications

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	High strength		
	Excellent appearance		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Electrical components		
	Printing press		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Molding Shrinkage - Flow (23°C)	0.30 - 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	83		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	54.0	MPa	ASTM D638
Tensile Elongation ² (Break)	18	%	ASTM D638
Flexural Modulus ³	3000	MPa	ASTM D790
Flexural Strength ⁴	92.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	120	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.20 mm)	450	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	130	°C	ASTM D648

1.8 MPa, unannealed, 6.40mm	122	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		UL 94
3.00 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110 - 120	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	235 - 260	°C	
Middle Temperature	240 - 270	°C	
Front Temperature	250 - 280	°C	
Processing (Melt) Temp	235 - 260	°C	
Mold Temperature	80.0 - 130	°C	
Back Pressure	0.00 - 10.0	MPa	
Injection instructions			
Processing Temperature Limit: 290°C Injection Speed: 60 to 90%			
NOTE			
1.	10 mm/min		
2.	10 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT