

FUDOWLITE® FC7910

Phenolic

Fudow Co., Ltd.

Message:

Examples of application

High-strength mechanical parts

Heavy electrical equipment parts

Automobile equipment parts

Electrical equipment structural parts

Weaving equipment parts

Ship components

Sealed equipment parts

General Information	
UL YellowCard	E46770-237196
Features	High strength
Uses	Electrical/Electronic Applications
	Electrical components
	Application in Automobile Field

Physical	Nominal Value	Unit	Test Method
Density	1.35 - 1.39	g/cm ³	JIS K7112
Molding Shrinkage	0.90 - 1.3	%	JIS K6911
Water Absorption (23°C, 24 hr)	0.25 - 0.45	%	JIS K6911
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	108		JIS K6911
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	59.0 - 69.0	MPa	JIS K6911
Flexural Modulus	7350 - 8340	MPa	JIS K7171
Flexural Stress	78.0 - 98.0	MPa	JIS K7171
Compressive Stress	176 - 196	MPa	JIS K6911
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.9 - 6.9	kJ/m ²	JIS K7111
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	160 - 170	°C	JIS K7191-1
Insulation Resistance			JIS K6911
after boiling	1.0E+8 - 1.0E+9	ohms	JIS K6911
at ordinary state	1.0E+10 - 1.0E+11	ohms	JIS K6911
Free Ammonia		%	JIS K7230
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	8.0 - 12	kV/mm	JIS K6911

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

