

EVICOM™ GA8/057

Flexible Polyvinyl Chloride

INEOS Compounds

Message:

BS 2571:90 Types E6, M6

Formulated without lead-based additives

Lead-free version of GA8/718

General Information	
Features	Good Flexibility
	Good Surface Finish
	Low (to None) Lead Content
Appearance	Opaque
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	BS 2782 620A
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	57		BS 2782 365B
BS Softness	86		BS 2782 365A
Cold Bend	-45	°C	BS 2782 151A
Cold Flexibility	-35	°C	BS 2782 150B
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	10.5	MPa	BS 2782 320A
Tensile Elongation (Break)	380	%	BS 2782 320A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT