# Mowital® B 16 H

### Polyvinyl Butyral

Kuraray Co., Ltd.

#### Message:

Characteristics

Polyvinyl butyral (PVB) grades with different molecular weights, and varying degrees of acetalization.

Recommended Uses

Binder for coatings (adhesion promotion/corrosion protection primers, shop primers, wash primers, stoving enamels, varnishes and lacquers for different substrates). Binder for printing inks. Co-binder for powder coatings. Temporary binder for ceramics. Binder for textile printing and non-woven. Wetting agent for grindings, esp. of organic pigments. Adhesives, pressure-sensitive adhesives and hotmelts.

General Information			
Features	Crosslinkable		
	Food Contact Acceptable		
	Heat Sealable		
Uses	Adhesives		
	Binder		
Agency Ratings	EU 2002/72/EC		
	EU 2004/19/EC		
	FDA 21 CFR 175.105		
	FDA 21 CFR 175.300		
	FDA 21 CFR 176.170		
Appearance	White		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Apparent Density	0.33	g/cm³	DIN EN 543
Water Absorption (20°C, 24 hr, 0.100 mm)	4.0 to 6.0	%	
Solution Viscosity <sup>1</sup>	14 to 20	mPa·s	DIN 53015
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	63.0	°C	ISO 11357-2
Additional Information	Nominal Value	Unit	Test Method
Non-Volatile Content	> 97.5	wt%	DIN 53216
Polyvinyl Acetate Content <sup>2</sup>	1.0 to 4.0	wt%	
Polyvinyl Alcohol Content <sup>3</sup>	18.0 to 21.0	wt%	
NOTE			
	According to Hoeppler, 10%		
1	solution in Ethanol containing 5% water at 20°C		
1.			
2.	Acetyl groups in terms of polyvinyl acetate		

3.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

