

SEQUEL® 1718-UV RXF

Polyolefin
LyondellBasell Industries

Message:

Sequel 1718-UV RXF thermoplastic polyolefin is designed for automotive exterior applications that require dimensional stability over a broad temperature range. This material exhibits excellent processability and low-temperature properties.

General Information			
Features	Good Dimensional Stability		
	Good Processability		
	Low Temperature Impact Resistance		
Uses	Outdoor Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.990	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	23	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Yield, 4.00 mm)	22.0	MPa	ISO 527-2/50
Flexural Modulus (4.00 mm)	1800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Instrumented Dart Impact ² (23°C)	19.0	J	ASTM D3763
NOTE			
1.	150x10x4 mm		
2.	2.20 m/sec		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT